



## DATE SHEET / SPECIFICATIONS CLEAN LDPE

CLEAN LDPE is a purge compound containing a high level of abrasive mineral additives and antioxidants based on LDPE. \*

This product is used to reduce cleaning times with PE or PVC in film extrusion, cables and moulding.

The compound remains relatively fluid and can be itself easily removed from the extruder or the injection machinery after purging.

### **SPECIFICATIONS**

<i>MFI (190°C, 2,16 kg)</i>	<i>1,5 – 3,0</i>	<i>M01-700**</i>
<i>Appearance</i>	<i>Opaque, greyish</i>	

\*\* Polytechs internal method

CLEAN LDPE contains abrasive and surfactant agents that clean mechanically and chemically the extruder from degraded PE, PVC and pigments from both the extruder and the die.

CLEAN LDPE is a filmable resin that will allow a continuous extrusion while purging.

It contains no toxic, volatile, or corrosive additives.

### **USAGE**

The use of CLEAN LDPE just before dismantling the equipment will reduce the cleaning time by more than 50%.

CLEAN LDPE allows as well to reduce significantly the amount of scrap generated when changing materials or colours.

We advise first to blend 50% of CLEAN LDPE together with the base resin of the last formulation and to reduce the temperatures and the speed of the screw.

Secondly, use 100% of CLEAN LDPE at 160°C while continuing to reduce temperatures.

At 140°C, purge for 10-20 minutes while increasing and reducing the screw speed in order to better clean the machine.

Finally, switch off the extruder or increase the temperatures to extrude the new material.

For start-up operations, purge the extruder at high and slow screw speeds for about 10 to 20 minutes with 100% of CLEAN LDPE and at 140°C.

CLEAN LDPE is only effective when used at low temperatures (100-180°C).

### **PACKAGING**

The product is packed in 25 kg PE bags on 1375 kg shrink-wrapped pallets.

\* *Other versions specially adapted for LLDPE, HDPE and PP are also available.*

**ED. 09/2004**